

TECHNICAL DATA SHEET

# 30810 AQUAVISION PU-WEIßLACK HOCHGLANZ



## AREA OF APPLICATION

SÜDWEST AquaVision PU-Weißlack Hochglanz is a high-quality paint based on alkyd PUR for coating work in interiors and exteriors. SÜDWEST AquaVision PU-Weißlack Hochglanz achieves surfaces with good flow properties and high durability. A test report in accordance with the DIN EN 71-3 inspection standard (European toy safety standard) is available.

## PROPERTIES

- Low-odour
- Easy application
- Very good non-sag properties
- Excellent flow properties
- Excellent hiding power
- Rapid drying
- High whiteness
- Excellent mechanical resistance
- Very easy to clean
- Block resistant

**COLOUR SHADE:** 9110 white

**CONTAINER:** 375 ml, 750 ml, 2.5 l

**COVERAGE:** approx. 80–100 ml/m<sup>2</sup>

**GLOSS LEVEL:** high-gloss (approx. 80–90 GU at 60°)

## AREA OF APPLICATION

### GENERAL RULES:

The substrate must be prepared and the coating work performed in accordance with the state of the art. All coatings and preliminary work should always be geared towards the project and the requirements it is exposed to. Please also observe the current BFS data sheets, published by the German Federal Committee for Paints and the Protection of Objects.

Also see German construction contract procedures (VOB), Part C, DIN 18363, Paragraph 3 "Painting and coating work". Treating/removing layers of paint by sanding, welding, burning off, etc. can cause harmful dust and/or vapours. Only carry out work in well-ventilated areas. Use appropriate breathing apparatus/protective equipment, if necessary.

All substrates must be clean, dry, load-bearing, and free from release agents. Substrates must be checked in terms of their load-bearing capacity and suitability for subsequent coatings. If necessary, create a test surface and test the adhesion by means of a cross cut and/or mesh tape tear-off. For coating build-ups, carry out intermediate sanding in between the individual coatings.

Sand grey and weathered wooden areas down to the load-bearing substrate. Clean and sand existing load-bearing paint coats. Round off sharp wooden edges. Ensure adequate drainage inclinations on horizontal surfaces. The moisture content for hardwood should be max. 12 % and for softwood max. 15 %. The drier the substrate, the greater the depth of penetration, improving the protective function and service life of subsequent paint coats. Wash tropical woods with constituents that delay the drying time with a cellulose thinner and apply a test coat.

## SUBSTRATE

Existing load-bearing coatings, dimensionally stable wooden components, primed substrates such as metals and plastics.

## SUBSTRATE PREPARATION:

### EXISTING LOAD-BEARING COATINGS:

Check for a firm hold. Completely remove existing non-load bearing coatings and build up again according to the substrate. Clean and thoroughly sand existing load-bearing coatings; prime any defects with SÜDWEST AquaVision All-Grund.

### NEW WOOD OR ENGINEERED WOOD, INTERIOR:

If necessary, prime with SÜDWEST AquaVision PU-Vorlack and fill as applicable.

### IRON AND STEEL, INTERIOR:

Carefully derust, degrease, and prime with SÜDWEST AquaVision All-Grund.

### ZINC AND HARD PLASTICS:

Clean with SÜDWEST Zink- und Kunststoff-Reiniger and prime with SÜDWEST AquaVision All-Grund.

### ALUMINIUM (NON-ANODISED) AND COPPER:

Clean with SÜDWEST Kupfer- und Alu-Reiniger and prime with SÜDWEST AquaVision All-Grund.

### PRIMED SUBSTRATES:

In order to achieve particularly high-quality surfaces in interiors, we recommend applying an intermediate paint coat with SÜDWEST AquaVision PU-Vorlack.

## APPLICATION

Stir well and apply with a brush or with a roller. Use tools that do not rust. Apply undiluted with a brush or with a roller. In order to achieve high-gloss surfaces, use SÜDWEST AquaVision PU-Weißlack Hochglanz for the intermediate and finishing coats.

Use a nonwoven abrasive that is as fine as possible to sand between coats.

#### APPLICATION CONDITIONS:

Temperature and humidity influence the drying process and flow of water-based coating materials.

Ideal application temperature 10–25 °C (approx. 60 % rel. humidity). The drying process is delayed by low temperatures and high humidity. Do not apply in conditions under +5°C. High temperatures and very low humidity shorten the cure time.

#### TOOL RECOMMENDATION:

For application by brush, we recommend using paint brushes with plastic fibre bristles. Foam rollers are suitable for rolling on small surfaces. On larger surfaces, apply the material with a microfibre paint roller, then go over immediately with a fine foam roller.

#### THINNING/TOOL CLEANING:

Clean water (drinking water quality). During longer breaks and at the end of work, wash the tools with water, then once again with soapy water, and rinse.

#### DRYING

(At 20 °C / 60 % rel. humidity, 100 µm wet-layer thickness).

Dust-dry and tack-free: approx. 2 h  
Over-coatable: approx. 16 h

Higher layer thicknesses and/or lower temperatures delay the drying times.

#### Note:

After 16 hours, SÜDWEST AquaVision PU-Weißlack Hochglanz can be sanded manually with a sanding pad. Before sanding larger surfaces by machine, we recommend a drying time of approx. 36 hours.

#### SPECIAL INFORMATION

SÜDWEST AquaVision PU-Weißlack Hochglanz has a tendency to yellow when exposed to artificial light or insufficient natural light. This is typical of the product and is therefore not a cause for complaint.

#### COLOUR RETENTION IN ACCORDANCE WITH BFS DATA SHEET NO. 26

Class: B, group: 1

#### EC DIRECTIVE 2004/42/EC:

The AquaVision PU-Weißlack Hochglanz product falls below the maximum VOC value of product category d (130 g/l) and is therefore VOC-compliant.

#### VDL DECLARATION

Alkyd emulsions, PUR dispersions, mineral white pigments, organic pigments, water, glycols, wetting agents, antifoam agents, polyurethane thickeners, driers, surface additives, sodium hydroxide, protection of the product during storage based on methylisothiazolinones and benzisothiazolinones

#### GISCODE BSW20

#### GENERAL SAFETY ADVICE

Good ventilation must be ensured while paints and varnishes are being applied and are drying. Keep away from food, drink, and animal feed. Avoid contact with skin and eyes. Do not breathe in dust during sanding work. Keep out of reach of children. Do not allow to enter ground water, bodies of water, or the sewer system in undiluted or large quantities.

Further information and the current SDS are available at [www.suedwest.de](http://www.suedwest.de)

#### STORAGE

Close opened containers so that they are airtight after use. Store in cool but frost-free conditions.

#### DISPOSAL

Only recycle empty containers. Dispose of them in accordance with legal requirements.

#### TECHNICAL CONSULTATION

Our sales representatives will be happy to answer any questions which have not been covered by this Technical Data Sheet. Our technical customer service team at the factory is also available to answer any detailed queries you may have. (06324/709-0).

#### DISCLAIMER

We are committed to taking the utmost care. However, we are only able to provide general information based on our own experiences, developments, and investigations, and these naturally cannot take the individual conditions of a project (substrates, weather conditions, other conditions) into account. The applicator is therefore obliged to maintain their knowledge in accordance with the state of the art and act responsibly. Our employees are available to provide specific advice and will be happy to do so. We accept no responsibility for the use of the product in combination with other products. The data provided in this Technical Data Sheet does not constitute binding information or liability. Furthermore, suspension or the appearance of a subsequent edition will invalidate this Technical Data Sheet; information about this can be accessed at any time on our website: [www.suedwest.de](http://www.suedwest.de).

STATUS: 2023/DECEMBER/KM