



TECHNICAL DATA SHEET

30450

STREICHLACK-ZUSATZ FÜR 2K-ALL-GRUND

AREA OF APPLICATION

Use SÜDWEST Streichlack-Zusatz für 2K-All-Grund as a hardener (component B) for SÜDWEST 2K-All-Grund (component A) when this is being applied to small surface areas with a paint brush.

Streichlack-Zusatz für 2K-All-Grund replaces both the hardener and the thinning agent. Due to the short open time, the product is only recommended for painting small surface areas or profiles. It is vital to work quickly, as initial drying is very quick.

COLOUR SHADE: colourless

CONTAINER: 250 ml

AREA OF APPLICATION

MATERIAL PREPARATION:

Wherever possible, the two components A and B should be mixed exactly in accordance with the specified **mixing ratio by volume**. Decant component A into a suitable container and add the required amount of Streichlack-Zusatz. This can be done in a cylindrical container with a measuring stick, for example. Stir vigorously then transfer to another container and mix thoroughly once again. Avoid mixing in large quantities of air if possible.

Mixing ratio: 4:1

(four parts component A to one part component B)

Pot life (+20°C / 60° rel. humidity)

The material has a pot life of approx. 2 hours once it is ready to use. Higher temperatures reduce pot life.

Do not continue to apply the material mixture once the pot life has expired.

Tool cleaning:

SÜDWEST 2K-Acryl-Verdünnung

DRYING (READY-TO-USE MATERIAL)

(+20°C / 60 % rel. humidity, after adding to SÜDWEST base components)

Dust-dry: after approx. 20 min

Fully dry: after approx. 24 hours

SPECIAL INFORMATION

Caution! Only for commercial users / experts. Contains isocyanates. May produce an allergic reaction. For more information about the safe use of the product, refer to the label and the current SDS.

EC DIRECTIVE 2004/42/CE

The Streichlack-Zusatz für 2K All-Grund product is out of scope of the VOC Directive.

VDL DECLARATION

Aromatic hydrocarbon mixtures, acetates, p-Toluenesulfonyl isocyanates, aliphatic polyisocyanates

GISCODE PU35

GENERAL SAFETY ADVICE

Only for commercial users / experts. Good ventilation must be ensured while paints and varnishes are being applied and are drying. Keep away from food, drink, and animal feed. Avoid contact with skin and eyes. Do not breathe in dust during sanding work. Only use in well-ventilated areas. Do not eat, drink, smoke, or inhale snuff tobacco during work.

Keep out of reach of children. Do not allow to enter the sewer system or bodies of water.

If rivers, lakes, or drains become contaminated, inform the relevant authorities in accordance with the local laws. Further information and the current SDS are available at www.suedwest.de

STORAGE

Close opened containers so that they are airtight after use. Store in cool but frost-free conditions.

DISPOSAL

Only recycle empty containers. Dispose of them in accordance with legal requirements.

TECHNICAL CONSULTATION

Our sales force will be happy to answer any questions which have not been covered by this Technical Data Sheet. Our technical customer service team at the factory is also available to answer any detailed queries you may have. (06324/709-0)

DISCLAIMER

We are committed to taking the utmost care. However, we are only able to provide general information based on our own experiences, developments, and investigations, and these naturally cannot take the individual conditions of a project (substrates, weather conditions, other conditions) into account. The applicator is therefore obliged to maintain their knowledge in accordance with the state of the art and act responsibly. Our employees are available to provide specific advice and will be happy to do so.

We accept no responsibility for the use of the product in combination with other products.

The data provided in this Technical Data Sheet does not constitute binding information or liability.

Furthermore, suspension or the appearance of a subsequent edition will invalidate this Technical Data Sheet;

information about this can be accessed at any time on our website: www.suedwest.de.

STATUS: 2023/AUGUST/KM