



TECHNICAL DATA SHEET

30044

AQUAVISION 2K-HÄRTER

AREA OF APPLICATION

Use SÜDWEST AquaVision 2K-Härter as component B for AquaVision 2K-Seidenmattlack (component A).

COLOUR SHADE: colourless

CONTAINER: 75 ml, 250 ml

COVERAGE: finished mixture: approx. 100–120 ml/m²

DENSITY:

AquaVision 2K Seidenmattlack 9110 white: approx. 1.2 kg/l

AquaVision 2K Seidenmattlack Basis 0000: approx. 1.1 kg/l

AquaVision 2K-Härter: approx. 1.0 kg/l

APPLICATION

MATERIAL PREPARATION:

Mix AquaVision 2K-Seidenmattlack (component A) with AquaVision 2K-Härter (component B) to a ratio of 10:1. Stir vigorously for 2–3 minutes. Homogeneous mixing of components A and B is a prerequisite for optimum film formation. Please ensure that the material around the edges of the container is mixed in well. Avoid mixing in large quantities of air if possible. Once mixing is complete, transfer the compound to a clean container and stir again. The mixture can be applied by volume or by weight. If you are working with small quantities, we recommend using a weighing scale to weigh out the components.

POT LIFE:

Once mixed, the material has a pot life. At a temperature of +20 °C, the pot life is approx. 6 hours. Higher temperatures reduce pot life.

Do not continue to apply the material mixture once the pot life has expired.

VDL (GERMAN PAINT AND PRINTING INK ASSOCIATION) DECLARATION:

Component B: carbodiimide

GISCODE: BSW30

GENERAL SAFETY ADVICE

Good ventilation must be ensured while paints and varnishes are being applied and are drying. Keep away from food, drink, and animal feed. Avoid contact with skin and eyes. Do not breathe in dust during sanding work. Keep out of reach of children. Do not allow to enter ground water, bodies of water, or the sewer system in undiluted or large quantities.

Further information and the current safety data sheet are available at www.suedwest.de

STORAGE

Close opened containers so that they are airtight after use. Store in cool but frost-free conditions.

DISPOSAL

Only recycle empty containers.

TECHNICAL CONSULTATION

Our sales representatives will be happy to answer any questions which have not been covered by this Technical Data Sheet. Our technical customer service team at the factory is also available to answer any detailed queries you may have. (06324/709-0).

DISCLAIMER

We are committed to taking the utmost care. However, we are only able to provide general information based on our own experiences, developments, and investigations, and these naturally cannot take the individual conditions of a project (substrates, weather conditions, other conditions) into account. The applicator is therefore obliged to maintain their knowledge in accordance with the state of the art and act responsibly. Our employees are available to provide specific advice and will be happy to do so. We accept no responsibility for the use of the product in combination with other products. The data provided in this Technical Data Sheet does not constitute binding information or liability.

Furthermore, suspension or the appearance of a subsequent edition will invalidate this Technical Data Sheet; information about this can be accessed at any time on our website: www.suedwest.de.

STATUS: 2023/SEPTEMBER/KM